

VESTOSINT® 5151 colored

Powder for fluidized bed coating

VESTOSINT 5151 colored are fluidized bed coating powders which are based on nylon 12 with integrated primer. Applications will be found e.g. for the coating of tubes in the water industry.

VESTOSINT® 5151 colored is available in

- black,
- white and
- pebble grey (referring to RAL 7032).

For more information we recommend our brochure "VESTOSINT – Polyamide 12 Coating Powder".

For further information please contact our experts of the department Marketing Development of the High Performance Polymers Business Unit.

Powder Information

Property	Test method		Unit	VESTOSINT 5151 colored
	international	national		
App. bulk density	ISO 60	DIN EN ISO 60	g/dm ³	= 320
Particle size distribution	< 32 µm < 100 µm < 250 µm	ISO 4610 DIN EN ISO 4610	Weight-%	= 4 30 – 60 100

Density, water absorption, thermal, mechanical and electrical properties

Property	Test method		Unit	VESTOSINT 5151 colored
	international	national		
Melting point	ISO 3146		°C	176
Density	23 °C ISO 1183		g/cm ³	1.06 ^{*)}
Shore hardness D	ISO 868			75
Ball indentation hardness	H30 ISO 2039-1		N/mm ²	101
Volume resistivity	IEC 60093		Ω · m	10 ¹²
Dielectric breakdown voltage	IEC 60243-1 K20/P50		kV/mm	85
Water absorption	ISO 62 100 °C, immersion		%	1.65
Moisture absorption	ISO 62 23 °C, 96 % r. h. 23 °C, 50 % r. h.		% %	1.2 0.5
Coef. of linear expansion	ISO 11359 23 – 55 °C	DIN 53752	10 ⁻⁴ · K ⁻¹	1.04
Thermal conductivity		Referring to DIN 52612	W/m · K	0.22 – 0.27
Specific heat		DIN 53765	J/g · K	2.27
Taber abraser	ASTM D 1242	DIN 53754	mg/100 turns	15

^{*)} Tested on unpigmented films with 300µm thickness.

® = registered trademark

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether expressed or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the products described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Degussa AG
High Performance Polymers
45764 MARL
GERMANY
Fax: +49 2365 49-5992
E-mail: vestosint@degussa